



Europäisches  
Patentamt

European  
Patent Office

Office européen  
des brevets

JP971 U.S. 1  
09/985859



066965  
1081

Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-  
gen stimmen mit der  
ursprünglich eingereichten  
Fassung der auf dem näch-  
sten Blatt bezeichneten  
europäischen Patentanmel-  
dung überein.

The attached documents  
are exact copies of the  
European patent application  
described on the following  
page, as originally filed.

Les documents fixés à  
cette attestation sont  
conformes à la version  
initialement déposée de  
la demande de brevet  
européen spécifiée à la  
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

00403080.5

Der Präsident des Europäischen Patentamts;  
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets  
p.o.

I.L.C. HATTEN-HECKMAN

DEN HAAG, DEN  
THE HAGUE, 12/10/01  
LA HAYE, LE



Europäisches  
Patentamt

Eur pean  
Patent Office

Office eur péen  
des brevets

**Blatt 2 der Bescheinigung**  
**Sheet 2 of the certificate**  
**Page 2 de l'attestation**

Anmeldung Nr.:  
Application no.:  
Demande n°: 00403080.5

Anmeldetag:  
Date of filing:  
Date de dépôt: 07/11/00

Anmelder:  
Applicant(s):  
Demandeur(s):  
ALCATEL  
75008 Paris  
FRANCE

Bezeichnung der Erfindung:  
Title of the invention:  
Titre de l'invention:  
Coating for optical fibers and method of manufacturing thereof

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:  
State:  
Pays:

Tag:  
Date:  
Date:

Aktenzeichen:  
File no.  
Numéro de dépôt:

Internationale Patentklassifikation:  
International Patent classification:  
Classification internationale des brevets:  
C03C25/10

Am Anmeldetag benannte Vertragsstaaten:  
Contracting states designated at date of filing: AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE/TR  
Etats contractants désignés lors du dépôt:

Bemerkungen:  
Remarks:  
Remarques:

## COATING FOR OPTICAL FIBERS AND METHOD OF MANUFACTURING THEREOF

### FIELD OF THE INVENTION

- 5 The present invention relates to a coating for optical fibers and a method of manufacturing thereof. More particularly the invention proposes a coating for optical fibers having graded properties so as to improve its resistance under mechanical constraints.

### 10 BACKGROUND OF THE INVENTION

- When optical fibers are subjected to mechanical constraints, their optical properties can decrease substantially. One of the main roles of a coating is that of protecting the fibers from such external perturbations. Thus the problem of obtaining a coating structure which could provide such protection
- 15 in an efficient manner has existed in the related art.

- A known solution is a single homogeneous layer for said coating. However as it is known, such single layer coating is not capable of providing an optimum resistance under a relatively high mechanical constraint. Due to these drawbacks, single layer coating was replaced by a double coating
- 20 technique using two different UV (ultraviolet) curing resins for coating, so as to provide a higher protection rate. In such structure, an internal layer having a glass transition temperature ( $T_g$ ) of no more than about  $-20^{\circ}\text{C}$  and preferably about  $-30^{\circ}\text{C}$  or even lower, and a Young's modulus lower than 2 MPa, preferably 1 MPa or even lower, prevents microbending and an
- 25 external layer with a relatively high  $T_g$ , generally approximately  $50^{\circ}\text{C}$  and a modulus of about one hundred times higher provides good resistance for fibers handling and cables manufacturing process and installation.

- Although the double layer structures have provided improvements in the mechanical properties of the fiber optic coatings, they still present the certain
- 30 drawback due to the fact that in order to obtain the appropriate mechanical properties the thickness of the overall coating is increased which is not a desirable consequence. Another drawback of such structure is that the associated costs for manufacture of the double layer coating become substantially high.

It is therefore desired to obtain a coating structure such that while the mechanical properties are appropriate so as to resist mechanical constraints, the overall thickness of the coating as well as its manufacturing costs are maintained at relatively low levels.

5

#### DESCRIPTION OF THE INVENTION

In order to overcome the above drawbacks, the coating for optical fibers and the method of manufacturing thereof, objects of the present invention are proposed. A typical optical fiber structure has a central core section which is  
10 the optical fiber itself, covered by a cladding section for example of silica. The coating as such covers the cladding section surrounding the outer surface of the latter. The coating proposed by the invention is of a so called graded modulus profile, meaning that the coating is configured so as to present a graded mechanical property as one moves outward from the  
15 interface between the cladding section and the coating material toward the outer (external) surface of the coating. The graded properties may thus be obtained by different procedure as will be explained in more detail further below.

Accordingly one object of the present invention is that of providing a coating  
20 for an optical fiber, comprising at least one partly crosslinked polymer, characterized in that the level of crosslinking increases according to the radial distance from an internal surface of the coating which interfaces with a cladding section of the fiber to the external surface of the coating.

According to an aspect of the present inventions there is provided the  
25 coating comprises a single resin characterized in that said resin is composed of a volatile, multifunctional and moderately reactive monomer dissolved in a fast curable oligomer, having a low modulus when polymerized.

A further object of the present invention is that of providing a method of manufacturing of a coated optical fiber comprising the steps of drawing of the  
30 fiber, deposition of the coating, cure of the coating and spooling of the optical fiber, characterized in that the coating comprises a single resin composed of a volatile, multifunctional and moderately reactive monomer dissolved in a fast curable oligomer, having a low modulus when polymerized and in that said monomer is not completely cured.

According to an aspect of the present invention said volatile monomer is evaporated before without being completely cured.

According to another aspect of the present invention ultraviolet irradiation is used for an incomplete curing of the single resin.

- 5 According to yet another aspect of the present invention electron beam irradiation is used for an incomplete curing of the single resin.

These and other features of the invention are discussed in further detail in the following description as well as in the claims.

10 BRIEF DESCRIPTION OF THE DRAWING

Figure 1 is a schematic representation of a cross-section of an optical fiber according to the invention with the level of cross-linking being represented as a variably shaded part.

15 EXAMPLE OF A PREFERRED EMBODIMENT

- As represented schematically in figure 1, a typical optical fiber structure has a core 1 which is located in the central part of the fiber structure and constitutes the optical fiber itself. Said central core section 1 is covered by a cladding section 2 which surrounds the surface of the core section completely as seen in the figure. The material used for such cladding section may be for example of silica. The coating 4 as such covers the cladding section 2 and in turn surrounds the outer surface of the latter completely. In such an arrangement, the internal surface 3 of the coating 4 interfaces the outer surface of the cladding. The coating 4 proposed by the invention is of a so called graded modulus profile, meaning that the coating 4 is configured so as to present a graded mechanical property as one moves outward from the interface 3 between the cladding section and the coating material toward the outer (external) surface of the coating 4. For the sake of illustration and better understanding of the object of the invention, such graded properties have been represented in figure 1 by a shaded area within the coating 4. The level of the darkness in the shaded area in the figure represents the of graded properties. Thus as it may be observed in the figure, the shaded intensity is increased, meaning increase in the level of cross-linking of the coating 4.
- 20
- 25
- 30

Therefore, according to the structure shown in figure 1, the graded modulus profile coating proposed by the invention is made in a graded configuration such that the mechanical properties of the coating 4 is gradually increased against external perturbation as one moves from the internal surface 3 of the coating 4 which interfaces with the cladding section 2 of the fiber, towards  
5 the external surface of the coating 4.

Preferably, the procedures proposed by the present invention for obtaining graded properties in the coating may comprise the following:

A homogeneous polymer may be exposed under an electron beam (EB)  
10 irradiation. As a result of such irradiation, the polymer is converted into a graded crosslinked matrix. This procedure would be convenient as long as the fiber core itself is not damaged, which in certain occasions may not be the case.

A second, and more advantageous procedure, which is proposed as a  
15 preferred embodiment of the present invention, is that of using UV (Ultraviolet) irradiation, which while provide the same results, does not cause any significant damage to the fiber core. Therefore, with a single resin as material for the coating layer, graded properties may be obtained by incomplete UV curing followed by inactivation or elimination of the residual  
20 reactive functions.

For example, a resin may be selected having a volatile, multifunctional and moderately reactive monomer, where volatile is understood to mean having a non zero partial vapor pressure at room temperature; the volatile monomer has a partial vapor pressure sufficiently high to be evaporated under vacuum  
25 (preferably between  $10^{-6}$  atm and 0.1 atm) at room temperature. The resin is dissolved in a fast curable oligomer, and having a low modulus when polymerized.

Next, the resulting polymer is deposited on a drawn optical fiber and put under a controlled curing process under an UV flux. The UV dose is lower  
30 than the dose which is required to fully cure the material. This procedure provides the so-called incomplete UV curing. As a result the polymer obtains graded mechanical properties with sufficient hardness so as to be wound on a spool without deformation. The excess of the unreacted monomer is then evaporated in a vacuum chamber. It is to be noted that during the curing  
35 process, the matrix itself is homogeneously cured, however the volatile

monomer is gradually cured, thus the evaporation of the monomer eliminates the part which is still uncured. This procedure gives rise to the fact that the level of cross linking increases gradually from the cladding-coating interface, i.e. the internal surface of the coating, toward the external surface of the same.

The following formulation information is provided as an exemplary manner and should not be construed as to limit the scope of the present invention, but only for the purpose of providing a better understanding of the same.

- 64% primary resin such as DeSolite® 3471-1-135;
- 10 - 32% reactive diluent, for example SR 206 from Sartomer (ethylene glycol dimethacrylate);
- 1% antioxidant, for example Ionol;
- 3% photoinitiator, for example Irgacure® 184 from Ciba;

The glass transition temperature is less than  $-40^{\circ}\text{C}$ .

- 15 Using the above formulation, thin films about 50  $\mu\text{m}$  may be cured in a variable speed UV conveyor and the excess reactive monomer is then evaporated under vacuum at room temperature. The resulting film provides mechanical properties which may be determined under compression tests, and which are different on the two surfaces of the film.

- 20 In this manner, a coating is obtained which while provides at least the same mechanical properties as the known double layer coatings, can present a thickness which can be lower, or at least the same as that of standard double layer coatings, but with improved mechanical properties compared to standard double layer coatings.

- 25 Further advantages of the present invention are that the cost of manufacture of the overall coated fiber is reduced due to a lower resin consumption, and the drawing speed of the fiber is increased under the same UV flux which is made possible because of the lower thickness of the resin.

- 30 It is to be noted that in the case of using EB irradiation, the procedure is substantially the same as that for UV irradiation, save for the use of EB instead of UV irradiation.

**CLAIMS**


- 1- Coating for an optical fiber, comprising at least one partly crosslinked polymer, characterized in that a level of crosslinking increases according to a radial distance from an internal surface (3) of the coating (4) which  
5 interfaces with a cladding section (2) to an external surface of the coating (4).
- 2- Coating of claim 1, comprising a single resin characterized in that said resin is composed of a volatile, multifunctional and moderately reactive monomer dissolved in a fast curable oligomer, having a low modulus  
10 when polymerized.
- 3- A method of manufacturing of a coated optical fiber comprising the steps of drawing of the fiber, deposition of a coating (4), cure of the coating (4) and spooling of the optical fiber, characterized in that the coating (4) comprises a single resin composed of a volatile, multifunctional and  
15 moderately reactive monomer dissolved in a fast curable oligomer, having a low modulus when polymerized and in that said monomer is not completely cured.
- 4- The method of claim 3, wherein said volatile monomer is evaporated before without being completely cured.
- 20 5- The method of claim 3 or 4, wherein ultraviolet irradiation is used for an incomplete curing of the single resin.
- 6- The method of claim 3 or 4 wherein electron beam irradiation is used for an incomplete curing of the single resin.



## COATING FOR OPTICAL FIBERS AND METHOD OF MANUFACTURING THEREOF

### 5 ABSTRACT

Coating for an optical fiber and method of manufacturing thereof, the coating comprising at least one partly crosslinked polymer having a level of crosslinking which increases according to a radial distance as one moves  
10 from the internal surface (3) of the coating (4) which interfaces with a cladding section (2) to the external surface of the coating (4). The coating comprises a single resin which is composed of a volatile, multifunctional and moderately reactive monomer dissolved in a fast curable oligomer, having a low modulus when polymerized.



**Fig. 1**